

# Stocklime 1600

1.6mm Stocklime / Calcium Carbonate



## High Grade Calcium Carbonate

## Natural Nutrition for Animal Feed

**DESCRIPTION:**

Quarried and Manufactured from our High-Grade Calcium Carbonate resource based at Angaston.

Barossa Quarries Stocklime 1600 is the ideal Calcium Carbonate supplement for animals.

Custom Milling Options Available

**TYPICAL CHEMICAL ANALYSIS:**

Calcium Carbonate: 94%  
 Silica: 2.7%  
 Magnesium Oxide: 0.5%  
 Fe<sub>2</sub>O<sub>3</sub>: 0.5%  
 Al<sub>2</sub>O<sub>3</sub>: 0.3%  
 Moisture: <0.1%

Particle Size Distribution		
Sieve (mm)	% Passing	Target
	Typical Analysis	% Passing
<b>1.600</b>	100.0	100.0
<b>1.180</b>	90.9	85 - 95
<b>0.600</b>	63.6	60 - 70
<b>0.300</b>	42.2	40 - 50
<b>0.150</b>	23.3	20 - 30
<b>0.075</b>	5.9	5 - 10
<b>-0.075</b>	0.5	0 - 5

**SIZES:**

A minus 1.6mm Stocklime / Calcium Carbonate

**BULK DENSITY:**

Loose (g/cm<sup>3</sup>): 1.60

**SPECIFIC GRAVITY:**

(g/cm<sup>3</sup>): 2.70

**PACKAGING:**

Bulk – Pneumatic Tanker or Bulk Tipper

Bulk Bag – Typically 1.2 tonne - Custom Sizing Available

20kg Packaged – 60 per Pallet

**TEST METHODS:**

Dry sieving on BS410 screens

AS1289 3.6.1



Associate Member of:



**FOR PRODUCT INFORMATION, SALES & CUSTOMER SERVICE**

**Email:** [info@barossaquarries.com](mailto:info@barossaquarries.com)

**Phone:** (08) 8564 2227

[www.barossaquarries.com.au](http://www.barossaquarries.com.au)

Radford Road, Angaston, SA, 5353

Please refer to the relevant Material Safety Data Sheet (MSDS) for health hazard information before handling or using this product

For Material Safety Data Sheets please email request to: [info@barossaquarries.com.au](mailto:info@barossaquarries.com.au)

DISCLAIMER: Ranges and values of trial sample testing or on a Technical Information Sheet are typical or expected ranges and are not guaranteed ranges. You must satisfy yourself that the product is suitable for the purpose for which you intend to use it. Barossa Quarries makes no representations as to suitability, fitness or merchantability.